

RESICHEM 512 UCEN 90 – chemical resistant coating at elevated immersion temperatures

Resichem 512 UCEN 90 is a high build solvent-free high functionality epoxy novolac coating designed to provide outstanding chemical and corrosion protection of steel and concrete structures at elevated temperatures. The coating has been designed to be applied using heated plural feed spray equipment and once cured will resist high concentration chemicals such as 98% sulphuric acid at immersion temperatures up to 75°C.

- Solvent free epoxy novolac coating
- Applied in a single coat using heated plural feed spray equipment
- Resistant to 98% sulphuric acid & 36% hydrochloric acid at 75°C in immersion conditions

Typical applications

Chemical containment	tank lining	process vessels
Chemical drains and channels	Internal pipe surfaces	sumps

Surface Preparation

Metallic Substrates

1. All oil and grease must be removed from the surface using an appropriate cleaner such as MEK.
2. All surfaces must be abrasive blasted to **ISO 8501/4 Standard SA2.5 (SSPC SP10/ NACE 2)** minimum blast profile of 75 microns (3mil) using an angular abrasive.
3. Once blast cleaned, the surface must be degreased and cleaned using MEK or similar type material.
4. All surfaces must be coated before gingering or oxidation occurs.

PLEASE NOTE: For salt contaminated surfaces the substrate must be pressure washed with clean water and checked for salt contamination, please refer to the surface preparation and pre-application guide for further information.

Existing Concrete

1. If the concrete surface is contaminated, pressure wash using clean water.
2. Once the concrete is dry, lightly abrasive blast or scarify taking care not to expose the aggregate.
3. Clean all dust and debris from the surface and prime with Resichem 503 SPEP (low viscosity epoxy primer).
4. Apply 503 SPEP at 150 microns (6mil) WFT, leave to cure for 3 hours (20°C/ 68°F) before overcoating.

New Concrete

1. Allow new concrete to cure for a minimum of 21 days and treat to remove any surface laitance.
2. Check the moisture content of the concrete prior to coating (8% moisture content or below).
3. Lightly scarify the surface taking care not to expose the aggregate.
4. Clean all dust and debris from the surface and prime with Resichem 503 SPEP (low viscosity epoxy primer).
5. Apply 503 SPEP at 150 microns (6mil) WFT, leave to cure for 3 hours (20°C/ 68°F) before overcoating.

Prior to Mixing & Application

Prior to mixing please ensure the following:

1. The base component is at a temperature between 25°C (77°F).
2. The ambient & surface temperature is above 10°C (50°F).
3. The ambient & surface temperatures are not less than 3°C (6°F) above the dew point.

Spray set up & Application

1. Spray application should be carried out by heated plural feed spray rig.
2. The temperature of the base component should be kept around 35°C (95°F).
3. Spray pressure of 3600psi and a tip size of 19-23 thou should be used.
4. Using a 50mm (2") wide synthetic brush, stripe coat all edges, joints, corners and equipment with the mixed material. The stripe coat must be approximately 100mm (4") wide, at 400 microns (16mil) wet film thickness.
5. Once the stripe coat has cured sufficiently and is capable of being overcoated, apply 512 UCEN 90 to all surfaces at 1000 microns (40mil) wet film thickness.

Coverage Rates

1ltr (0.25 US gallon) of fully mixed product will give the following coverage rates –

2.5m² at 400 microns 26ft² at 16mil

16ltrs (4.2 US gallon) of fully mixed product will give the following coverage rates –

16m² at 1000 microns 171ft² at 40mil

Please note that the coverage rates quoted are theoretical and do not take into consideration the profile or condition of the surface being repaired.

Resimac Ltd, Unit B, Park Barn Estate, Station Road, Topcliffe, Thirsk, YO7 3SE, United Kingdom

Tel: +44 1845 577498 Email: info@resimac.co.uk Web: www.resimacsolutions.com

TDS512UCEN90.rv2.10122018

Cure Times

At 20°C (68°F) the applied materials should be allowed to harden for the times indicated below before being subjected to the conditions indicated. These times will be extended at lower temperatures and reduced at higher temperatures:

Usable life	15 minutes
Minimum overcoating time	4 hours
Maximum overcoating time	12 hours
Water/ sea water immersion	4 days
Chemical immersion	7 days

For Optimum Performance

After an initial curing period of at least 12 hours at 20°C (68°F), raising the cure temperature progressively to 60 - 80°C (140-175°F) for up to 8 hours will result in improved mechanical, thermal and chemical resistance properties

Pack Sizes

This product is available in the following pack sizes –
1ltrs (0.25 US gallon), 16ltrs (4.2 US Gallons).

Colour

Base component – Grey or Red
Activator component – Amber

Over-coating times

Minimum - the material can be over-coated as soon as it is touch dry, approximately 4 hours at (20°C (68°F)).

Maximum - the over-coating time should not exceed 12 hours.

Where the maximum over-coating time is exceeded, the material should be allowed to harden before being abraded or flash blasted to remove surface contamination.

Storage Life

5 years if unopened and store in normal dry conditions (15-30°C/ 60-86°F)

Other Technical Documents

Quick Application Guide	-	Spray applications
Safety Data Sheets	-	Base & Activator components
Product Specification Sheet	-	Technical Performance Information

Health and Safety

Please ensure good practice is observed at all times. Protective gloves, goggles & a disposable coverall must be worn during the mixing and application of this product. Before mixing and applying the material ensure you have read the fully detailed Safety Data Sheet.

Legal Notice:

The data contained within this Technical Data Sheet is furnished for information only and is believed to be reliable at the time of issue. We cannot assume responsibility for results obtained by others over whose methods we have no control. It is the responsibility of the customer to determine if the product is suitable for use. Resimac accepts no liability arising out of the use of this information or the product described herein.