

RESICHEM 552 CSM MEMBRANE

Resichem 552 CSM

Membrane is a single component high build water based acrylic waterproof coating. The product is a high performance waterproofing membrane with long term UV stability.

Typical applications

The product is used as an embedment coating with glass fibre chop strand matting on roof surfaces

Characteristics

Appearance

Single Component:

Thixotropic
acrylic
emulsion

Mixing Ratio

Single Component

Density

1.25

Solids content

60%

Sag Resistance

Nil at 1500 microns

Coverage

Brush or roller applications:

The material can be applied in a range of thicknesses dependent on the application.

750 microns WFT

1.33m² per ltr

1500 microns WFT

0.66m² per ltr

Cure Times

The applied material should be allowed to harden for the times indicated below before being subjected to the conditions indicated:

Touch Dry

10°C	2-4 hours
20°C	1-2 hours
30°C	30-60 minutes
40°C	15-30 minutes

Minimum overcoating time

10°C	6-8 hours
20°C	3-4 hours
30°C	1.5-2 hours
40°C	45-60 minutes

Maximum overcoating time

Indefinite

Storage life

5 years if unopened and stored in normal dry conditions (15-30°C)

Mechanical Properties

Elongation

Tested to ASTM D412
160%

Tensile Strength

Tested to ASTM D412
42kg/cm² (600psi)

Direct Pull Adhesion

Tested to ASTM D4541
28kg/cm² (400psi)

Water

Permeability

Tested to ASTM D1653
2 x 10⁴ perm.cm

Vapour

Heat Resistance

Resistant to dry heat up to 120°C dependent on load.

Quality

All Resimac Products are supplied under the scope of the company's fully documented quality system.

Warranty

Resimac warrants that the performance of the product supplied will conform to the typical descriptions quoted within this specification provided material is stored correctly and used according to the procedures detailed in the Technical Data Sheet for the material.

Health and safety

Please ensure good practice is observed at all times during the mixing and application of this product. Protective gloves and other recommended personal protective equipment must be worn during the mixing and application of this product. Before mixing and applying the material please ensure you have read and fully understood the detailed Material Safety Data Sheet

Legal Notice: The data contained within this Product Specification is furnished for information only and is believed to be reliable at the time of issue. We cannot assume responsibility for results obtained by others over whose methods we have no control. It is the responsibility of the customer to determine the products suitability for use. Resimac accepts no liability arising out of the use of this information or the product described herein.